

TEST REPORT

Results of Tests on brick Conducted in accordance with ASTM C67/C67M-18 Standard Test Methods for Sampling and Testing Brick and Structural Clay Tile 01/28/2022

			01/28/	2022			
Name:	Glen-Gery Technical Services 433 South Pottsville Pike Shoemakersville, PA, 19555-0340			Plant: Sampled Date: Fired Date:	Pittsburgh Pla 01/12/2022 01/03/2022	nt	
Phone: (p) (610) 562-3 Report Number: GGHRP645		3076 ve Extruded Cored					
Description:	Clay w/Additiv	e Extruded Co					
Absorption		1	2	3	4	5	Average
24 Hour Cold Water (%) 5 Hour Boiling Water (%) Saturation Coefficient		1.4 1.6 0.86	1.5 1.7 0.88	1.4 1.5 0.88	1.3 1.5 0.9	1.4 1.6 0.88	1.4 1.6 0.88
Compressive Strength		1	2	3	4	5	Average
	psi MPa	19,017 131	18,125 125	18,598 128	18,146 125	18,411 127	18,459 127
IRA (Oven Dried Method) g/min/30 in. ²		1	2	3	4	5	Average
		1.3	1.9	1.5	1.5	1.6	1.6
Efflorescence		1	2	3	4	5	
Efflorescence Detection		Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

ASTM 32 - 13 Standard Specification for Sewer and Manhole Brick (Made from Clay or Shale) Grades: SM - SS / MM - MS

ASTM 62 - 17 Standard Specification for Building Brick (Solid Masonry Units Made From Clay or Shale) Class: SW - MW - NW

ASTM 216 - 19 Standard Specification for Facing Brick (Solid Masonry Units Made From Clay or Shale) Grades: SW - MW

CSA - A82-14 Fired Masonry brick made from clay or shale Class: EG - IG

Mike Krzyzanowski Technical Services Manager





BRICKWORI